

POLYKEN[®] #939 Filler Mastic

System Description

The Polyken filler tapes are designed as an underlying filler material prior to the application of Polyken coating systems and Covalence Heat Shrinkable Products. The elastomeric formulation is very conformable, making it ideal for filling in transition areas around tees, ells, valves, specials, welded and coupled field joints. The filler tapes maintain flexibility over a wide temperature range and under various conditions encountered in the field.

Product Features/Benefits

- Flexible under various field conditions
- Easy and simple application

- Conformable and moldable
- Compatible with Polyken coating systems

System Products

Polyken #939 Filler Mastic

The #939 is a thick mastic-like butyl rubber filler designed to fill and smooth transition areas. The semi-tacky composition remains flexible and is easily molded in filler to conform around irregular shapes. #939 comes in rope and flat tape form in a variety of thicknesses to meet almost any job requirement.

Product Properties

Color	Black
Elongation	>600%
Solids Content	100%
Penetration Hardness	85 - 105 DMM
(ASTM D217)	(300 gm moving load)
Low Temperature Flexibility	No cracking when bent around a 1 inch mandrel
	@ -23°C
Chemical Resistance	No visible deterioration after 30 days immersion in the following solutions:
	5% Caustic Potash
	5% HCL
	5% H2S04
	Saturated HS
Maximum Operating Temperature	85°C

Ordering Information

description	thickness	width	length	rolls/case	cases/pallet	rolls/pallet
939-125 Tape	3.2 mm (0.125")	50.8 mm (2 ")	6.1 M (20 ft)	12	54	648
939-500 Rope	11.2 mm (0.44")	11.2 mm (0.44 ")	6.6 M (21.75 ft) 8	24	192
939-750 Rope	15.2 mm (0.6 ")	16.8 mm (0.66 ")	4.4 M (14.5 ft)	8	40	320
939-1000 Rope	22.6 mm (0.89")	22.6 mm (0.89 ")	4.4 M (14.5 ft)	6	40	240
939-1250 Rope	26.3 mm (1.03")	31.8 mm (1.25")	4.4M (14.5 ft)	4	45	180
939-2000 Rope	40.6 mm (1.6 ")	46.7 mm (1.84 ")	2.3 M (7.5 ft)	4	40	160

The leading global partner in protecting the integrity of critical infrastructure.



-

corrosion protection group

The reacting global parties in protecting the integrity of critical matter determine the set of the integrity of the integrit

Headquarters Franklin, MA, USA Tel: +1 508 918 1714 US Toll Free: +1 800 248 0149 Fax: +1 508 918 1910 CPG@berryplastics.com

Houston, TX, USA Tel: +1 713 676 0085 US Toll Free: +1 888 676 7202 Fax:+1 713 676 0086 CPGH@berryplastics.com Tijuana, Mexico Tel USA +1 858 633 9797 Fax US: +1 858 633 9740 Tel Mexico: +52 664 647 4397 Fax Mexico: +52 664 607 9105 CPGTJ@berryplastics.com Local Distributor / Representative: MESA PRODUCTS 4445 SO 74 E AVE TULSA, OK 74145 For contact details of local Distributors / Representatives Please visit www.berrycpg.com.

Westerlo, Belgium

Tel. +32 14 722500

Fax +32 14 722570

CPGE@berryplastics.com

Baroda, India Tel: +91 2667 264721 Fax: +91 2667 264724 CPGIN@berryplastics.com