



Oxbow Calcining International LLC

**Industrial Products
Sales Office**
1450 Lake Robbins Drive
Suite 500
The Woodlands, Texas 77380
Telephone (281) 907-9400
FAX (281) 907-9466

CarboCoke[®] 400

<i>Typical Properties of CarboCoke[®] 400</i>	
Sulfur	4.0%
Fixed Carbon	97%
Electrical Resistivity	0.04 ohm-inch
Bulk Density	52-57 lbs/ft³
Moisture	0.2%

*Typical Sizing is – 20 Mesh
Special Sizing May Be Available Upon Request*

**** Preferred Grade as a Carbon Backfill for Cathodic Protection Applications**

PRODUCT DESCRIPTION

Petroleum Coke blended, calcined and packaged under strict control over the entire production process. To optimize product availability, we maintain one of the industry's most sophisticated materials management systems as well as custom packaging options.

STANDARD PACKAGING

*Multi-wall labeled 50# paper bags, 45 or 50 bags/pallet
2000# Supersacks
Bulk Truck and Rail*

ISO 9001 CERTIFIED

IMPORTANT: While the information and data contained in this promotional literature is presented in good faith and believed to be reliable, it does not constitute part of our terms and conditions of sales unless specifically incorporated in our Order Acknowledgement. NOTHING HEREIN SHALL BE DEEMED TO CONSTITUTE A WARRANTY, EXPRESSED OR IMPLIED, THAT THIS INFORMATION OR DATA IS CORRECT OR THAT THE PRODUCTS DESCRIBED HEREIN ARE MERCHANTABILITY OR FIT FOR A PARTICULAR PURPOSE, OR THAT THIS INFORMATION, DATA OR PRODUCTS CAN BE USED WITHOUT INFRINGING PATENTS OF THIRD PARTIES.